

LINER HS yellow, red, blue, black, green

acrylic solventborne road marking paints

Symbol : 24.30.12-50.00
Standard: ZN-PCW-1230:2007

Properties:	LINER HS “colours” acrylic solventborne road marking paint is a suspension of pigments and fillers immersed in a solution of acrylic resin and organic solvents with an addition of additives.												
Range of application:	LINER HS “colours” paint is used for selected horizontal road marking applications such as: pedestrian crossings, bicycle trails and as special markings for pedestrian zones and areas of slow traffic, as temporary applications and for overlaying existing road markings during roadworks.												
Application methods:	The marking can be applied with all kinds of application machines (pneumatic and hydrodynamic application machines).												
Consumption:	On good substrates, proper marking parameters can be obtained using 600g of the marking for every m ² . Most commonly, the consumption comes to 600g to 800g for every m ² . A maximum volume of 900g of the marking can be used for 1m ² .												
Functional properties:	<p>The marking is characterised by a short drying time, high density and very good coverage. It adheres well to the substrate, is highly resistant to abrasion and conditions of atmospheric exposure and has good roughness. Applying glass reflective micro beads makes the marking highly visible in the headlight beam of a vehicle in night conditions. Because the micro beads adhere strongly to the paint, the coating maintains its reflective properties under conditions of use for a very long time.</p> <p>General technical information:</p> <table> <tr> <td>Colour</td> <td></td> <td>yellow, red, blue, black, green</td> </tr> <tr> <td>Density in 20°C</td> <td>[g/cm³]</td> <td>1,55÷1,60</td> </tr> <tr> <td>Viscosity</td> <td>KU</td> <td>78 – 82</td> </tr> <tr> <td>Solid content</td> <td>[%]</td> <td>75 ÷ 79</td> </tr> </table>	Colour		yellow, red, blue, black, green	Density in 20°C	[g/cm ³]	1,55÷1,60	Viscosity	KU	78 – 82	Solid content	[%]	75 ÷ 79
Colour		yellow, red, blue, black, green											
Density in 20°C	[g/cm ³]	1,55÷1,60											
Viscosity	KU	78 – 82											
Solid content	[%]	75 ÷ 79											
Drying time:	In close to optimal conditions i.e. at an ambient temperature of about 20°C and substrate temperature of 25°C, using 700 g/m ² of the marking and with an air humidity of below 80%, the drying time required before traffic can be resumed is 25 minutes. The drying time can extend in lower temperatures and different humidity or if more of the paint is applied.												
Thinner:	WPZ 11 solvent for road marking paints.												
Application method:	LINER HS “colours” is to be applied onto dry, clean and coherent bituminous substrate. Due to the risk of yellowing of the paint it is not recommended to apply it on pitch type substrates. Before application, the contents of the packaging have to be carefully stirred to obtain a uniform consistency. The viscosity the marking comes in needs not be modified. Only if the viscosity of the paint rises significantly due to e.g. a low ambient temperature (5-10°C) can it be thinned using a small amount of WPZ 11 solvent at a volume of 2% w/w. Using excessive amounts of the thinner is unacceptable as it causes a deterioration of the coating quality. The marking												

	is to be applied at a temperature range of 5-35°C for both the air and substrate and at a relative humidity of the air not exceeding 80%. The paint cannot be applied in conditions of fog or dew. The paint can be applied using pneumatic or hydrodynamic application machines.
Packaging:	30 kilogram metal buckets.
Warranty:	12 months from the production date if stored in its original packaging and not exposed to direct sunlight.
H&S and fire safety guidelines:	The paint is highly flammable and contains hazardous volatile solvents, that is why during application general H&S and fire safety regulations have to be followed . In particular it is forbidden to smoke cigarettes or consume food during application. The paint has to be stored in tightly sealed packagings, away from any sources of fire, heat and direct sunlight exposure. For more detailed information refer to the Material Safety Data Sheet.

LINER HS - colours